



**Europäisches  
Patentamt**

**European  
Patent Office**

**Office européen  
des brevets**

PCT/EP 03/50913

#2

02.12.0.

REC'D 19 JAN 2004	
WIPO	PCT

**Bescheinigung**

**Certificate**

**Attestation**

Die angehefteten Unterlagen stimmen mit der ursprünglich eingereichten Fassung der auf dem nächsten Blatt bezeichneten europäischen Patentanmeldung überein.

The attached documents are exact copies of the European patent application described on the following page, as originally filed.

Les documents fixés à cette attestation sont conformes à la version initialement déposée de la demande de brevet européen spécifiée à la page suivante.

**Patentanmeldung Nr. Patent application No. Demande de brevet n°**

02406084.0

**PRIORITY  
DOCUMENT**  
SUBMITTED OR TRANSMITTED IN  
COMPLIANCE WITH RULE 17.1 (a) OR (b)

Der Präsident des Europäischen Patentamts;  
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets  
p.o.

**R C van Dijk**



Anmeldung Nr:  
Application no.: 02406084.0  
Demande no:

Anmeldetag:  
Date of filing: 10.12.02  
Date de dépôt:

Anmelder/Applicant(s)/Demandeur(s):

Ciba Specialty Chemicals Holding Inc.  
Klybeckstrasse 141  
4057 Basel  
SUISSE

Bezeichnung der Erfindung/Title of the invention/Titre de l'invention:  
(Falls die Bezeichnung der Erfindung nicht angegeben ist, siehe Beschreibung.  
If no title is shown please refer to the description.  
Si aucun titre n'est indiqué se référer à la description.)

Mixtures of fluorescent whitening agents

In Anspruch genommene Priorität(en) / Priority(ies) claimed / Priorité(s)  
revendiquée(s)  
Staat/Tag/Aktenzeichen/State/Date/File no./Pays/Date/Numéro de dépôt:

Internationale Patentklassifikation/International Patent Classification/  
Classification internationale des brevets:

D06L3/00

Am Anmeldetag benannte Vertragstaaten/Contracting states designated at date of  
filing/Etats contractants désignées lors du dépôt:

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR IE IT LI LU MC NL PT SE SI SK

Mixtures of Fluorescent Whitening Agents

The present invention relates to mixtures of fluorescent whitening agents (FWAs) based on dicyano-1,4-bis-styrylbenzenes and bisbenzoxazoles.


Fluorescent whitening agents are often used in the form of mixtures of two or more components, since such mixtures may exhibit a higher degree of whiteness than that of the sum of the individual components alone.

Thus, for example, GB 2200660 describes mixtures of 2,3'-, 2,4'- and 4,4'-dicyano-1,4-bis-styrylbenzenes, although the composition is restricted by the method of preparation, whilst US 5695686 describes similar asymmetric mixtures containing further isomers again due to the process of preparation.


According to EP 44 996, high degrees of whiteness can also be achieved by application of mixtures of specific bisbenzoxazoles.

The constitution of such mixtures of FWAs is important not only in regard to their whitening effects, but also with regard to the shade, which may be more or less bluish, reddish or greenish, the desirability being a matter of utmost importance to the end user.


It has now, surprisingly, been found that high degrees of whiteness in especially desirable bluish shades are obtained from mixtures of fluorescent whitening agents comprising 5 to 60% by weight of a compound of formula



and 40 to 95% by weight of one or more compounds of formula



wherein  $R_1$  denotes hydrogen,  $C_1$ - $C_8$ alkyl,  $C_5$ - $C_{14}$ aryl or  $C_6$ - $C_{24}$ aralkyl and X is a bivalent radical of formula (3), (4) or (5)



Furthermore, mixtures comprising 7.5 to 45% by weight of the compound of formula (1) and 55 to 92.5% of the compound of formula (2) are of particular interest.


The compounds of formulae (1) and (2) are well-known FWAs and commercially available or can be prepared according to well-known methods.

$C_1$ - $C_8$ alkyl as  $R_1$  includes for example methyl, ethyl, propyl, isopropyl, n-butyl, isobutyl, sec-butyl, tert-butyl, amyl, tert-amyl (1,1-dimethylpropyl) n-pentyl, neopentyl, and n-hexyl.


Examples for  $C_5$ - $C_{14}$ aryl are phenyl, tolyl, mesityl, isityl, xylyl, naphthyl, anthryl and phenanthryl.

$C_6$ - $C_{24}$ aralkyl as  $R_1$  includes for example benzyl, 2-phenylethyl, diphenylmethyl, naphthylmethyl and 2-naphthylethyl.

Preferably, the mixtures according to the invention contain a compound of formula (1a)





Further preferred mixtures according to the invention contain a compound of formula (2a)



wherein  $R_1$  and X are as defined above.

Preferred compounds of formula (2a) are those wherein  $R_1$  denotes hydrogen or  $C_1$ - $C_8$ alkyl.

Especially preferred are the compounds of formulae (2b) and (2c).



Particularly preferred mixtures according to the invention contain 30 to 50 % by weight, most preferably 35 to 45 % by weight, of a compound of formula (1a) and 50 to 70 % by weight, most preferably 55 to 65 % by weight, of a compound of formula (2b).

Further particularly preferred mixtures according to the invention contain 7.5 to 30 % by weight, most preferably 8.0 to 25 % by weight, of a compound of formula (1a) and 70 to 92.5 % by weight, most preferably 75 to 92 % by weight, of a compound of formula (2c).

Further objects of the present invention are the use of the mixtures of the compounds of the formulae (1) and (2) for whitening synthetic fibres, in particular polyester fibres, said compositions containing a mixture comprising 5 to 60% by weight of a compound of formula 1 and 40 to 95% of a compound of formula (2).

As is customary with mixtures of fluorescent whitening agents, the individual components can be processed to the commercial form by dispersing them in a liquid medium, preferably water. This can be done by dispersing the individual components and then combining the dispersions so obtained. However, it is also possible to mix the individual components together in substance and then to disperse them jointly. The dispersing operation is carried out in a conventional manner in ball mills, colloid mills, bead mills or the like.

The present invention thus further provides brightener compositions containing water and, in each case based on the weight of the formulation, from 3 to 25% by weight, preferably from

10 to 20% by weight of the above defined fluorescent whitening agent mixture and also 0 to 60%, preferably 5 to 50% by weight, of auxiliaries.

Suitable auxiliaries include, for example, dispersing and wetting agents, antifreezes, antifoams, thickeners/stabilizers and biocides.

Examples for anionic dispersants are condensates of aromatic sulfonic acids as well as ligninsulfonates, alkyl aryl sulfonates, alkyl diphenyl oxide sulfonates, sulfates or phosphates of ethoxylated alkyl phenols, di- or tristyrylphenols.

Examples for non-ionic dispersants are ethylene oxide adducts with fatty alcohols, higher fatty acids, alkyl phenols, sorbitol esters, di- and tristyrylphenol; copolymers of ethylene oxide and propylene oxide or ethylenediamine ethylene oxide/propylene oxide adducts.

Examples for thickeners/stabilizers are copolymers of N-vinylpyrrolidone with 3-vinylpropionic acid, polyvinylalcohols or non-ionic/anionic polysaccharides.

All types of formulation auxiliaries are described in McCutcheon's year books of Emulsifiers & Detergents and Functional Materials.

The mixtures of this invention and the compositions containing them are suitable for whitening textile materials made from synthetic fibres, in particular, those made from linear polyesters. However, these mixtures and compositions can also be used for whitening blends that contain linear polyesters.

The mixtures of this invention are applied by the methods normally employed for the application of fluorescent whitening agents, for example, by the exhaust dyeing process in dyeing machines or by pad-thermofixation. The treatment is conveniently effected in an aqueous medium in which the compounds are present in finely particulate form as suspensions, microdispersions or, as the case may be, solutions. If appropriate, dispersants, stabilisers, wetting agents and other assistants can be added during the treatment. The treatment is normally carried out in the temperature range from about 20°C to 140°C, preferably 110 to 130°C, for example, at the boiling temperature of the bath or in the proximity thereof. Where the mixtures are applied by the pad-thermofixation process, the thermofixing is preferably carried out at a temperature of between 170 and 200°C.




The mixtures according to the invention provide a blue shade without the addition of shading dyes.

Furthermore, the materials treated with the mixtures according to the invention exhibit a high lightfastness as well as a high whiteness level and excellent brilliancy.

The following Examples serve to illustrate the invention; parts and percentages are by weight, unless otherwise stated.

### Examples

Polyester fabrics are treated with mixtures containing the compounds of formulae (1a) and (2b) or (2c), respectively, and analysed with respect to degree of whiteness according to Ganz, lightfastness according to ISO 105-B02, tint value TV according to Ganz-Griesser, lightness  $L^*$  according to the CIELAB system and brightness B (D65) according to ISO 2470. The results are summarised in Tables 1a, 1b, 2a and 2b.



### Example 1

#### a) Application on Polyester in Exhaust Process

A polyester fabric (prescoured, heat-set at 195°C, 165 g/m<sup>2</sup>) is treated, in a dyeing apparatus, at room temperature and at a liquor ratio of 1:20, with an aqueous bath containing a mixture of the optical brightening agents of formula (1a) and (2b) or (2c), respectively, in the ratios given in Table 1, in finely dispersed form and in the presence of 1g/l of a fatty alcohol polyglycol ether as dispersing agent. The temperature is raised from

room temperature to 130°C over 30 minutes, held for a further 30 minutes at this temperature and subsequently cooled to 40°C during 15 minutes. The textile material is then rinsed for 30 seconds under running water and dried at 70°C.

**Table 1a:**

FWA Mixture	Concentration	Ganz Whiteness	Lightfastness
(2b) + (1a) (60:40)	0.07 %	215	6 – 7
(2c) + (1a) (80:20)	0.09 %	206	7
(2c) + (1a) (90:10)	0.10 %	205	7 - 8

**b) Application on Polyester in Pad-bake Process**

A polyester fabric (prescoured, heat-set at 195°C, 165 g/m<sup>2</sup>) is treated at room temperature by the pad-bake process with an aqueous liquor containing a mixture of the optical brightening agents of formula (1), (2a) or (2b), respectively, in the ratios given in Table 1, in dispersed form and in the presence of 1g/l of an alkali salt of a sulfonated dicarboxylic acid alkyl ester. The liquor pick-up is 50%. Subsequently, the fabric sample is dried for 30 minutes at 70°C and then thermofixed during 30 seconds at 180°C.

**Table 1b:**

FWA Mixture	Concentration	Ganz Whiteness
(2b) + (1a) (60:40)	0.95 g/l	203
(2c) + (1a) (80:20)	1.20 g/l	200
(2c) + (1a) (90:10)	1.35 g/l	205

**Example 2**

A polyester fabric (prescoured, heat-set at 195°C, 165 g/m<sup>2</sup>) is treated by the exhaust process and by the pad-batch process, respectively, as described in Example 1.

The Ganz whiteness, tint value, lightness and brightness of the treated samples are given in Tables 2a and 2b.

**Table 2a (exhaust process):**

FWA Mixture	Concentration	Ganz Whiteness	TV	L*	B (D65)
(2c) + (1a) (80:20)	0.09 %	206	0.58	97.68	111.2
(2c) + (1a) (90:10)	0.10 %	205	0.41	97.70	110.5




Table 2b (pad-bake process):


FWA Mixture	Concentration	Ganz Whiteness	TV	L*	B (D65)
(2c) + (1a) (80:20)	1.8 g/l	200	0.84	97.36	112.3
(2c) + (1a) (90:10)	2.0 g/l	205	1.08	97.83	110.1

# Claims




1. A mixture of fluorescent whitening agents comprising 5 to 60% by weight of a compound of formula



and 40 to 95% of one or more compounds of formula




wherein R<sub>1</sub> denotes hydrogen, C<sub>1</sub>-C<sub>8</sub>alkyl, C<sub>5</sub>-C<sub>14</sub>aryl or C<sub>8</sub>-C<sub>24</sub>aralkyl and X is a bivalent radical of formula (3), (4) or (5)




2. A mixture according to claim 1 comprising 7.5 to 45% by weight of the compound of formula (1) and 55 to 92.5% of the compound of formula (2).

3. A mixture according to claim 1 or 2 comprising a compound of formula (1a)



4. A mixture according to any of claims 1 to 3 comprising a compound of formula (2a)



wherein R<sub>1</sub> and X are as defined in claim 1.

5. A mixture according to claim 4 comprising a compound of formula (2a) wherein R<sub>1</sub> denotes hydrogen or C<sub>1</sub>-C<sub>8</sub>alkyl.

6. A mixture according to claim 4 comprising a compound of formula (2a) wherein R<sub>1</sub> denotes methyl and X is a bivalent radical of formula (3).

7. A mixture according to claim 4 comprising a compound of formula (2a) wherein R<sub>1</sub> denotes hydrogen and X is a bivalent radical of formula (4).

8. A composition, which contains water, mixtures of fluorescent whitening agents according to any one claims 1 to 7 and, optionally, auxiliaries.


9. A composition according to claim 8 containing water and, in each case based on the total weight of the formulation, from 3 to 25% by weight, preferably from 10 to 20% by weight of the above defined fluorescent whitening agent mixture and 0 to 60%, preferably 5 to 50% by weight, of auxiliaries.

10. Use of a mixture according to any one of claims 1 to 7 or a composition according to claim 8 or 9 for whitening synthetic fibres.


11. Use of a mixture according to any one of claims 1 to 7 or a composition according to claim 8 or 9 for whitening polyester fibres.

**Abstract**




The present invention relates to a mixture of fluorescent whitening agents comprising 5 to 60% by weight of a compound of formula



and 40 to 95% of a compound of formula



wherein  $R_1$  denotes hydrogen,  $C_1$ - $C_8$ alkyl,  $C_5$ - $C_{14}$ aryl or  $C_6$ - $C_{24}$ aralkyl and X is a bivalent radical of formula (3), (4) or (5)



compositions containing the mixture and the use of the compositions for whitening synthetic fibres, in particular, polyester.